







## Plastic Primer

Vehicolor Plastic Primer is specially formulated to prepare plastic surfaces for the application of primers, topcoats, and adhesives. It offers excellent ease of use, fast drying, and superior adhesion without the need for sanding. Designed for both automotive refinishing and industrial use, this primer ensures reliable bonding on a wide range of plastic substrates, delivering a smooth, ready-to-coat surface with minimal effort.

### PROCESS

	Substrates	Vehicolor Plastic Primer can be applied over AAS, PC/PET, PETP, PP-E and PP+E/P.
	Mixing ratio (Weight)	Vehicolor Plastic Primer is a ready for use product.
	Spray gun tips	Spray gun: 1.2-1.3 mm Conventional: 2 bar/26-29 psi inlet HVLP: 2 bar/26-29 psi inlet
	Spray method	Coats: 1 normal coat Flash-Off Time: At 20°C, 15-20 before overcoating.
	Drying time	15-20 minutes at 20°C
	Sanding	Not required.

### NOTE

1. For full Health and Safety information please refer to Material Safety Data Sheet (MSDS)
2. Observe the precautionary notices displayed on the container.
3. Good ventilation must be provided in the working environment.
4. 2 years in unopened containers when stored in cool, dry conditions.